



**PLASTICS & NON-METALLICS
FOR INDUSTRY SINCE 1921**

FRANKLIN FIBRE – LAMITEX CORPORATION
P.O.Box 1768, Wilmington, DE 19899

Phone: (302) 652-3621
Fax: (302) 652-3621
e-mail: info@franklinfibre.com

Franklin Vulcanized Fibre Tube Performace Data

Tensile Strength:	840 kg/sq-cm (1,196 psi) for a wall thickness less than 1/32 inch when the OD is less than 2.0 inches.		
Density:	Minimum 1.35 g/cm ³ with production material varying 1.38 to 1.40 g/cm ³		
Compressive Strength:	Wall thickness 1/32 inch to 1/8 inch:	770 kg/sq-cm	1,095 psi
	Wall thickness 1/8 inch to 5/16 inch:	840 kg/sq-cm	1,195 psi
Dielectric Strength	Wall thickness less than 1/16 inch:	175 Volts/cm	
	Wall thickness 1/16 inch to 1/18 inch:	150 Volts/cm	
	Wall thickness 1/8 inch to 5/16 inch:	100 Volts/cm	
Water Absorption (% after 24 hours)	Wall thickness 1/32 inch to 1/8 inch:	75%	
	Wall thickness 1/8 inch to 1/4 inch:	50%	
	Wall thickness 1/4 inch to 5/16 inch:	25%	
Ash Content:	Red 3.5%, White 3.5%, Grey 1.5%, Black 1.5%		
Zinc Chloride Content:	Minimum 0.03% and Maximum 0.07%		

All values are average test results from typical production material. No warranty is implied or guarranteed and testing is recommended for each application.

Epoxies • Phenolics • Melamine • Silicone • Sheets • Molded Shapes • Tubes • Cut to Size • Fabricated Parts

FRANKLIN FIBRE – LAMITEX CORPORATION